

JS-750-T

PRODUCT DATA SHEET



Product Code

JS-750-T

General Description

The JS-750 wear resistant compound steel plate has been developed for applications requiring high resistance against wear by abrasion combined with Middle impact.

High Chromium carbide special designed for extremely wear application with low impact.

Chemical Composition of Deposited Metal (Wt. %)

	C	Si	Mn	Cr	Fe
Typical	≥4.0%	≥0.53%	≥1.8%	≥25.0%	Rem

General Characteristics

Type of alloy	Iron based
Group of alloys	High chromium iron
Microstructure	Primary carbides and M7C3 eutectic carbides in an austenitic matrix
Typical hardness range	HRC 60-62
Cracking	Yes
Abrasion	Excellent
Impact resistance	Moderate to low
Typical service temperature	Up to 300°C
Machining	Only Grinding
Flame cutting	No - Plasma-arc is the generally preferred method of cutting

Areas of industrial use

The JS-750-T wear plate are used in many segments of industry: Steelworks, Dredging, Mining, Refineries, Cement, Glass, Timber, Power Generation Plants, Earthmoving, Sugar Mills, etc.

Typical fields of applications

Sieve of scatter grader	Suction and discharge dredge pipes
Reclaimer protecting plate	Screw conveyors
Chutes and decks of all types and sizes	Catalyst feed nozzles
Vertical mill protecting parts	Chain conveyor wear plates
Cyclones	Side protecting plate of pressure roller
Chopping cone inner liners	Shovel bucket wear liners
Crusher liners	Fan blade and housing liners
Coal mill classifier cones	Bottom ash screws
Inner housing of air lock	V shape separator wear plate
Vibratory feeders	Pump shells and pump impellers
Hopper liners	Feed pipes and lift pipes

Phone: +86-775-4552662/3

FAX: +86-775-4552661

E-mail: JS-MACHINERY@163.com

Add: JiangNan industrial area, Guigang City, Guangxi Province, China

Value evolved from solution